UTILIZATION OF SOME NON-EDIBLE OILS AS FATLIQUORING PRODUCTS IN LEATHER TANNING

Alfawal, G. S. 1; Nofal, Z. A. 1; A. E. Khattab 1 and A. I. Nasr 2

1 Biochemistry Department, Faculty of Agriculture, Azhar University, Cairo, Egypt.

2 Wool Production and Technology Department, Desert Research Center, Cairo, Egypt.

Key Words: castor, fatliquor, jatropha, non-edible oils, plant oil, sulphation, used frying oil.

ABSTRACT

Fatliquor affects the physical properties of the leather and makes it more flexible and softer. This study was carried out to utilize some nonedible oils, Castor, Jatropha and Used Frying Oil (UFO), to prepare sulphated fatliquor, can be used in leather tanning. The used oils in this study were obtained by automatic hydraulic press. The sulphated fatliquors emulsions were prepared by sulphitation of oils with concentrated sulfuric acid. Chemical characterizations of oils and prepared fatliquor were determined. Prepared fatliquors were compared with commercial fish oil fatliquor (stander) at two concentrations, 6% and 12% based on the pelt weight. All fatliquors were used in fatliquoring calf wet-blues to study the change in leather properties. Results explained that the fat content in Castor seeds and jatropha seeds were 29.94% and 51.67%, respectively. The content of unsaturated fatty acids were 67.13%, 81.28% and 50.10% in extracted oils of Castor, Jatropha and UFO respectively, the iodine value of extracted oils from them which was (90.68 gm. I₂/100 gm. oil), (103.17 gm. I₂/100 gm. oil) and (70.58 gm. I₂/100 gm. oil) respectively. Therefore, oils - which are liquid - are rich in unsaturated fatty acids. Iodine value indicates to a melting point of the extracted oils. So fats and oils are usually classified, on the basis of their iodine value as drying oils, semi-drying oils and non-drying oils. Also existence of the double bond in the acids makes the sulfation reaction easy through breaking that bond and completing the reaction which was suitable for preparing fatliquor for leather tanning. After fatliquoring the calf wet-blues with different studied fatliquors and finishing it, the properties of finished leathers were similar in quality and suitable for different purposes of leather manufacturing. Therefore, the study is recommended to utilize studied fatliquoring in leather tanning to decrease the production cost of leathers, as well as, reducing pollution resulting from unsafe disposal of these oils.

INTRODUCTION

Leather tanning is a general term for the numerous processing steps involved in converting animal hides or skins into finished leather. The process aims to isolate collagen by removing non-collagenous components of skin and then making it resistant to physical, chemical and biological factors, in addition to protecting it from drying. (Burgess 1994 and Varnali 2004).

Hence, various chemical and mechanical treatments are applied to produce finished leather. Among leather chemical additives, fatliquoring agents are one of the most effective chemicals to impart softness and flexibility to leather and their use is critical to attaining the required characteristics for leather and its products. Fatliquoring is an oil-addition process by which the leather fibers are lubricated. Thus after drying, fibers will be capable of slipping over one another and produce an adequate compliance and softness (Akpan et al., 2006).

Fatliquoring process is considered very important in leather finishing due to maintain the fibers without drying and reduces frictional forces within the fiber weaves, thus allowing the fibers to move laterally over each other (**Kronick**, 1998). Additionally, it improves the leathers quality in mechanical properties, fullness, soft handle, flexibility and pliability, as well as, keeps leather's colors steady and more appealing (**Nashy** *et al.*, 2011).

Fatliquoring step is done by adding biological and/or non-biological fatty substances. Using different non-traditional resources for producing leathers fatliquors is important to produce leathers with various properties, in addition to utilize these resources (BASF, 2007).

Castor plant (*Ricinus communis*), belonging to the family (*Euphorbiaceae*) and it grows naturally over a wide range of geographical and climatic regions **Omari** *et al.*, (2014).

Akpan et al., (2006) reported that Castor oil is a nonedible oil crop, pale amber viscous liquid and non-drying oil with mild or no odor or taste. Chemically, it is a triglyceride which is a glycerol molecule with each of its three hydroxyl group esterified with a long clown fatty acid. Its major fatty acid is the unsaturated, hydroxylated 12-hydroxy, 9-octadecenoic acid, known familiarly as ricinoleic acid. The fatty acid composition of a typical castor oil contains about 87% of ricinoleic acid. In addition, castor seeds contains about 30-35% oil, which can be extracted from castor seeds by either mechanical pressing or solvent extraction or combination of them.

Jatropha plant (*Jatropha curcas*) is a potential anti-feedant candidate, belongs to the family (*Euphorbiaccae*). The seed which is black and oval in shape is rich in fixed oil **Shukla** et al., (1996).

Also **Akintayo** (**2004**) reported that jatropha oil contains 47.25% of crude oil and 5.54% of moisture content. The high iodine value of it (105.2 gm. I₂/100 gm. oil) is caused by high content of unsaturation fatty acid 78.5% such as oleic acid and linoleic acid.

Adebowale and Adedire (2006) noted that the percentage of oil is high (66.4%) which golden yellow, it much higher than those recorded for most oil-rich seeds and this would therefore be an advantage in terms of the exploitation of the oil in producing.

On the other hand; **El-Shattory** *et al.*, **(2012)** reported that Jatropha tree has been successfully cultivated in Egypt as it can grow well in the desert as it withstand drought and can be irrigated with treated sewage water since its oil is nonedible. Jatropha seeds contain nonedible viscous oil which can be used for several industrial applications. So, this work explores usage of the non-edible Jatropha fatty acids as a fatliquoring agent in order to save the needed edible fats and oils for food purposes.

In frying oils, which ever type the oil, it is usually heated to about 170° C to 220° C. When the oil is heated to these temperatures in the presence of oxygen (air), the oil undergoes thermal, physical and chemical degradation by reaction (Moreira *et al.*, 1999). Thus, frying is an intense process that induces a multitude of chemical reactions in the frying medium and generates a plethora of chemical compounds **Belitz** *et al.*, (2004).

Also **Romero** *et al.*, (2006) found that the amount of degraded products increases with the duration of heating at high temperature. Therefore, the more the oil is heated, the more degradation takes place and the more toxic compounds are formed in the oil.

Megahed and Nashy (2010) reported that the application of the discarded palm oil as "used frying oil" in leather industry as fat-liquoring agent. Fatliquors helped to prevent the loosening of leather grain and ugly appearance of chrome tanned leather after drying. In addition, fatliquoring process improves leather characteristics such as soft handle, full, flexibility, and pliability as well as enhancement its mechanical properties.

Idun-Acquah et al., (2016) reported that the degradation in the physico-chemical properties of the plant cooking oil after repetitive

frying. We conclude that repetitive use of plant oil safe 1-2 times of batch frying after that should be avoided since changes in physicochemical properties of the oil affect oil quality for human consumption so used frying oils not suitable for human consumption would be suitable for alternate uses..

Habib and Alshammari (2017) studied recycling and application of the used frying oil in the leather industry as a fatliquoring agent. The oil was sulfated at optimal conditions and evaluated in order to verify their capacity to be used as a leather fatliquoring agent using different concentrations (4, 6, 8 and 10% of sulfated oil). The analytical data reveal that the aqueous solution of 10 % sulfated oil (fatliquor emulsion) show a high degree of stability against metallic ions and pH as well as great ability to penetrate the chrome tanned leather, adding mass to the leather.

Therefore, this study aimed to using Castor, Jatropha and Used Frying Oil (UFO) as non-traditional resources of biological oils to produced leather fatliquors and comparing it with fish oil fatliquor (stander), which commercially used in tanneries.

MATERIALS AND METHODS

This study was divided into two main parts, preparing fatliquor emulsion from plant oils, and then testing prepared fatliquor emulsions in leather fatliquoring process. The finished leather was tested physically and chemically after completing finishing steps.

1. Preparing fatliquors emulsions from oils:

About 10 Kg Castor and Jatropha seeds were collected from several local farms at Al-Buhaira Governorate, Egypt and several Agricultural companies at Ismailia city, Egypt, respectively. Seeds were packed in polyethylene packages and stored in deep freezer at -18 ± 2 °C.

The Castor and Jatropha oils were prepared from collected seeds by automatic hydraulic press in National Research Center, Dokki, Giza according to **Allawzi** *et al.* (1998), while UFO was collected from several restaurants at Cairo, Egypt.

Sufficient amounts of oils were used in producing fatliquor emulsions as follows:

• Castor fatliquor:

According to **Tawfig** *et al.*, (2017) 15% of concentrated sulfuric acid (98%) was added based on oil weight as drops on the castor oil. During addition, the oil was stirred at 18-20°C. The sulfation process was carried out slowly for about 3 hrs. A saturated sodium chloride solution

was added to the resultant products and mixed with them. The mixture was then kept in a separating funnel overnight to separate the layers. The upper layer was neutralized to pH 5.0 by adding sodium hydroxide solution (30%) to produce the fatliquor.

• Jatropha and UFO fatliquors:

According to **Habib and Alshammari** (2017), 15% of concentrated sulfuric acid 98% was added based on oil weight as drops on Jatropha or UFO oil. The overall reaction time was 2 hrs. During the addition of acid, the reaction temperature was controlled below 30°C by low stirring and slowly adding sulfuric acid. The sulfated oil was washed with 10% sodium chloride solution at room temperature and neutralized to pH 6.7-7.2 using 30% aqueous solution of sodium bicarbonate with agitation for 30 min.

After preparing different fatliquors, chemical properties were determined in seeds, extracted oils and prepared fatliquor emulsions. NIR analysis, moisture and fat contents were determined in plant seeds, while identification of fatty acids, iodine value, and saponification value and acid value were determined in extracted oils. On the other hand, moisture content, ash content, pH, density, fatliquor stability in different solutions and fatliquor substance were determined in fatliquor emulsions prepared.

2. Testing prepared fatliquor emulsions in leather tanning:

Prepared fatliquor emulsions were used in fatliquoring leathers at El-Shafei son's tannery in El-Max region, Alexandria, Egypt. Eight wetblues from calves were divided into 8 groups (4 fatliquors X 2 concentrations) as show in Table (1). All leathers were close in thickness and size, which graded as grade I.

Table (1): Different e	experiments (of fatlio	uoring	leathers.
------------------------	---------------	-----------	--------	-----------

C	Concentrations of fatliquoring materials							
Groups	Castor oil	Jatropha oil	Used frying oil	Fish oil				
1	6%	-	-	-				
2	12%	-	-	-				
3	-	6%	-	-				
4	-	12%	-	-				
5	-	-	6%	-				
6	-	-	12%	-				
7	-	-	-	6%				
8	-	-	-	12%				

Firstly, wet blues were shaved by shaving machine to decrease the thickness from the flesh side into approximately 0.9 mm. After then, wet blues were ready for the next steps as follows in table (2).

After finishing, chemical, physico-mechanical and organoleptic properties of the finished leather were determined on finished leathers according to standard procedures (ASTM, 2010). The properties were leather thickness, tensile strength, elongation, split tear strength; fat, moisture, ash and pH.

Table (2): Finishing steps recipe for studied calf wet-blues.

1 1		steps recipe for si			1	
Process	%	Chemical	TIME	C	pН	OPERATION
	200	H2O				Check grease
Degreasing	1	OXALIC				Drain + Wash
	0.2	SOAP	60			21000 1 77000
	150	H2O		3 5		
Retanning	1	BLACK HH200	10			Drum speed 5
Keianning	2	F G L AMX	30			cycle/min.
	2	SINTICROMO				
	2	CROME 33	60			
Fixation	1.5	SOD. FORMATE	90	Ove	er Nigh	nt & Drain + Wash
	150	Н2О		3 0		
M 4 1 4	2	LECOSIN CDD				Check pH=5.5-6
Neutralization	0.8	SOD. FORMATE	20			Drain + Wash
	0.5	NAHCO3	40		5.5	
	4	LECOREN 200	40			
	80	Н2О		3		
	3	F G L R7S				
ъ.	3	SMITH SF156				GI I
Dyeing	2.5	FGL CN-NEW				Check
	4	BLACK AF 135	60			penetration
	5	MIMOSA				
	5	QUBRARCHO	60			
	100	H2O		7		
Fatliquoring				0		
	2.5	F G L F88	20	1		Same path
	X	X		<u> </u>		
	2	ECOSOFT 1001	60			
Fixation	2	FORMIC	2X10+5 0			overnight Check pH = 3.5- 4 next day Drain + Wash

RESULTS AND DISCUSSION

The chemical composition of plant seeds:

Results in table (3) show the chemical composition of plant seeds by Near Infrared analyzer. The moisture content in Castor and Jatropha seeds was considered low 5.79% and 7.81% respectively, where fat content was very high 32.04% and 55.74% respectively. The highest oil

yield or content probably might be due to the type of plant or the type of soil and the climate.

Table (3): The chemical composition of seeds by Near Infrared analyzer.

Seeds	The chemical composition %								
Seeus	Moisture	Fat	Protein	Ash	Fiber	Carbohydrates	Total		
Castor	5.79	32.04	23.87	5.43	23.65	9.22	100%		
Jatropha	7.81	55.74	7.64	4.89	19.91	4.01	100%		

Identification of fatty acids of extracted oils by (GLC) analyzer:

Results in table (4) show the identification of fatty acids of extracted oils by gas liquid chromatography analyzer which can be divided into two main groups as illustrated in the table. The saturated fatty acids content in castor, Jatropha and used frying oil were 29.44%, 16.70% and 47.80% respectively, where unsaturated fatty acids content were 67.13%, 81.28% and 50.10% respectively. The ratios of total saturated fatty acids to the total unsaturated fatty acids were 1:2.28, 1:4.87 and 1:1.05 respectively.

Table (4): Fatty acid composition of extracted oils by (GLC) analyzer.

anaryzer.								
	Fatty ac	ids	Perc	entage of fatty	acids %			
			Castor	Jatropha	Used frying			
				1	oil			
	C14:0	Myristic acid	0.00	0.00	0.34			
	C15:0	Pentadecanoic acid	0.11	0.00	0.00			
	C16:0	Palmitic acid	9.70	9.55	30.20			
Saturated	C17:0	Margaric acid	0.70	0.14	0.11			
Saturateu	C18:0	Stearic acid	11.41	6.76	16.45			
	C20:0	Arachidic acid	6.45	0.22	0.32			
	C22:0	Behenic acid	1.07	0.03	0.38			
		Total	29.44%	16.70%	47.80%			
	C16:1	Palmitolic acid	0.09	0.72	0.10			
	C17:1	Margoleic acid	0.05	0.06	0.05			
	C18:1	Oleic acid	32.54	47.41	27.67			
Unsaturated	C18:2	Linolic acid	28.20	32.14	15.65			
	C18:3	Linolenic acid	3.02	0.85	6.40			
	C20:1	Gadoleic acid	3.23	0.10	0.23			
	Total		67.13	81.28	50.10			
	Unknov	vn	3.43%	2.02%	2.10%			
	Total		100%	100%	100%			

From these results, major fatty acid is higher content of the unsaturated fatty acids which suitable for using in leather fatliquoring (Covington, 2009).

Characterization of Extracted oils:

From data in table (5), extracted oils shows that the oils can be used in leather fatliquroing according to scales range introduced by **BASF** (2007). The iodine, saponification and acid values for extracted oils were near similar to the corresponding values of palm oil, neatsfoot oil and beef tallow fats, which used already in leather fatliquoring (Covington, 2009).

For this chemical composition and characterization of extracted oils; it can be concluded the ability of converting their fats into sulphated fatliquor emulsions.

Table (5):	Characte	erization	of	Extracted	oils.
---------	-----	----------	-----------	----	------------------	-------

	Characteristics									
Oils	Extraction yield (%)	Iodine value (gm. I ₂ /100 gm. oil)	Saponification value (mg KOH/gm. oil)	Acid value (mg KOH/gm. oil)	Density (gm./cm³)	Colour				
Castor	25	90.68	192.36	2.12	0.95	Pale yellow mild				
Jatropha	40	103.17	197.04	3.48	0.93	Dark greenish yellow				
used frying	-	70.58	200.69	1.51	0.79	Dark brown				

Characterization of prepared fatliquoring emulsions:

Fish oil fatliquor is considered from the most commercial sulphated fatliquor used in leather tanning (**BASF 2007**). For that samples from prepared sulphated fatliquors and commercial fish oil fatliquor were taken to compare their chemical characterizations. The results were tabled in Table (6).

Table (6): Characterization of prepared fatliquoring emulsions.

Chamataristics	-	Eigh ail		
Characteristics	Castor	Jatropha	Used frying oil	Fish oil
Preparation Yield (%)	151.00	178.00	143.00	-
Moisture (%)	37.00	41.00	38.00	54.60
Ash (%)	2.91	2.65	2.47	0.80
Fatliquor Substances (%)	60.09	56.35	59.53	44.60
Density (gm./cm ³)	0.93	0.90	0.89	0.85
pH (10% aqueous solution)	7.16	7.00	7.33	8.00

The moisture was lower in prepared fatliquors than commercial fish oil fatliquor that might be due to the efficiency of washing step, which was done after sulphitation reaction for fats. While the ash values were higher in prepared fatliquors. The density values were similar

approximately, while pH (10% aqueous solution) was lower in prepared fatliquors than commercial fish oil fatliquor.

Testing prepared fatliquor emulsions in leather tanning:

The results were showed in Table (7). Regarding to physical properties of finished calf leathers, both prepared and fish oil fatliquors exhibited similar effect on all physical properties of corresponding finished leathers. With respect to the concentration effect of adding fatliquor, an increase of concentration caused an increase in values of all physical properties almost (Tensile Strength, elongation, tearing and thickness).

Table (7): Physical properties of calf leathers.

$ \begin{array}{ c c c c c } \hline Item & N & Thickness \\ (mm) & Strength \\ (mm) & Strength \\ (kg/cm^2) & (\%) & (kg/cm) \\ \hline \hline \\ \hline $	= 0000 ()	,	2200	z properties (of call leathers.			
Titem N (mm) Strength (kg/cm²) (%) (kg/cm²) (kg/cm²)				T1.: .1	Tensile		Tearing	
$ \begin{array}{c c c c c c c c c c c c c c c c c c c $	Iten	1	N		Strength	Elongation	Strength	
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$				(mm)	(kg/cm ²)	_	(kg/cm)	
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$						ct		
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	Caste	or	8	1.20 ± 0.015 b	204.43 ± 16.28 a	45.93 ± 2.60	18.33 ± 0.97 °	
$ \begin{array}{c c c c c c c c c c c c c c c c c c c $	Jatrop	ha	8	1.15 ± 0.015 °	214.91 ± 16.28 a	51.97 ± 2.60	21.96 ± 0.97 b	
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	Used fryi	ng oil	8	1.26 ± 0.015^{a}	200.40 ± 16.28^{a}	51.16 ± 2.60		
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	Fish	oil	8	1.23 ± 0.015 ab	141.29 ± 16.28 b	42.78 ± 2.60		
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	g	œ	•	0.000	0.017	0.061	0.000	
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	Signi	ficance		**	*	NS	**	
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$					Concentration E	ffect		
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	6%	1	16	1.23 ± 0.011^{a}	172.08 ± 11.51^{b}	45.78 ± 1.84	20.74 ± 0.69 b	
Significance * * NS * Castor oil 6% 4 $1.20 \pm 0.02^{\text{ bc}}$ $184.38 \pm 23.02^{\text{ ab}}$ 46.86 ± 3.68 $17.97 \pm 1.38^{\text{ d}}$ oil 12% 4 $1.20 \pm 0.02^{\text{ bc}}$ $224.48 \pm 23.02^{\text{ ab}}$ 44.99 ± 3.68 $18.70 \pm 1.38^{\text{ d}}$ Jatroph a oil 6% 4 $1.18 \pm 0.02^{\text{ cd}}$ $203.02 \pm 23.02^{\text{ a}}$ 46.27 ± 3.68 $19.34 \pm 1.38^{\text{ cb}}$ Used frying oil 4 $1.13 \pm 0.02^{\text{ d}}$ $226.80 \pm 23.02^{\text{ a}}$ 57.67 ± 3.68 $24.57 \pm 1.38^{\text{ ab}}$ How the street of the street oil	12		16	1.19 ± 0.011^{b}	208.44 ± 11.51 ^a	50.14 ± 1.84		
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	G**6*		0.046	0.035	0.107	0.016		
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	Sigili	Significance		*	*	NS	*	
$\begin{array}{c ccccccccccccccccccccccccccccccccccc$								
Jatroph a oil 6% 4 $1.18 \pm 0.02^{\text{ cd}}$ $203.02 \pm 23.02^{\text{ a}}$ 46.27 ± 3.68 19.34 ± 1.38 Used frying oil 6% 4 $1.13 \pm 0.02^{\text{ d}}$ $226.80 \pm 23.02^{\text{ a}}$ 57.67 ± 3.68 24.57 ± 1.38 12% 4 $1.28 \pm 0.02^{\text{ a}}$ $181.55 \pm 23.02^{\text{ ab}}$ 47.79 ± 3.68 $28.27 \pm 1.38^{\text{ ab}}$ 12% 4 $1.25 \pm 0.02^{\text{ ab}}$ $219.26 \pm 23.02^{\text{ a}}$ 54.54 ± 3.68 $26.73 \pm 1.38^{\text{ ab}}$ Fish oil 6% 4 $1.25 \pm 0.02^{\text{ ab}}$ $119.37 \pm 23.02^{\text{ b}}$ 42.20 ± 3.68 $17.37 \pm 1.38^{\text{ d}}$ Fish oil 12% 4 $1.20 \pm 0.02^{\text{ bc}}$ $163.21 \pm 23.02^{\text{ ab}}$ 43.36 ± 3.68 23.04 ± 1.38 Significance 0.001 0.042 0.076 0.000	Castor	6%	4	1.20 ± 0.02 bc		46.86 ± 3.68		
Jatroph a oil 0.76 4 1.13 ± 0.02^{-d} 226.80 ± 23.02^{-a} 57.67 ± 3.68 24.57 ± 1.38 ab Used frying oil 6% 4 1.28 ± 0.02^{-a} 181.55 ± 23.02^{-ab} 47.79 ± 3.68 28.27 ± 1.38^{-a} 12% 4 1.25 ± 0.02^{-ab} 219.26 ± 23.02^{-a} 54.54 ± 3.68 26.73 ± 1.38^{-a} Fish oil 6% 4 1.25 ± 0.02^{-ab} 119.37 ± 23.02^{-b} 42.20 ± 3.68 17.37 ± 1.38^{-d} Fish oil 12% 4 1.20 ± 0.02^{-bc} 163.21 ± 23.02^{-ab} 43.36 ± 3.68 23.04 ± 1.38 bc Significance 0.001 0.042 0.076 0.000	oil	12%	4	1.20 ± 0.02 bc	$224.48 \pm 23.02^{\text{ a}}$	44.99 ± 3.68	18.70 ± 1.38 d	
a oil 12% 4 $1.13 \pm 0.02^{\text{ d}}$ $226.80 \pm 23.02^{\text{ a}}$ 57.67 ± 3.68 $24.57 \pm 1.38^{\text{ ab}}$ Used 6% 4 $1.28 \pm 0.02^{\text{ a}}$ $181.55 \pm 23.02^{\text{ ab}}$ 47.79 ± 3.68 $28.27 \pm 1.38^{\text{ a}}$ frying oil 12% 4 $1.25 \pm 0.02^{\text{ ab}}$ $219.26 \pm 23.02^{\text{ a}}$ 54.54 ± 3.68 $26.73 \pm 1.38^{\text{ ab}}$ Fish oil 12% 4 $1.25 \pm 0.02^{\text{ ab}}$ $119.37 \pm 23.02^{\text{ b}}$ 42.20 ± 3.68 $17.37 \pm 1.38^{\text{ d}}$ Fish oil 12% 4 $1.20 \pm 0.02^{\text{ bc}}$ $163.21 \pm 23.02^{\text{ ab}}$ 43.36 ± 3.68 $23.04 \pm 1.38^{\text{ bc}}$	Jatroph	6%	4	1.18 ± 0.02 ^{cd}	203.02 ± 23.02 a	46.27 ± 3.68		
	_	12%	4	1.13 ± 0.02^{d}	226.80 ± 23.02 a	57.67 ± 3.68		
	Used	6%	4	1.28 ± 0.02 a	181.55 ± 23.02 ab	47.79 ± 3.68	28.27 ± 1.38 a	
Fish oil 12% 4 $1.20 \pm 0.02^{\text{ bc}}$ $163.21 \pm 23.02^{\text{ ab}}$ 43.36 ± 3.68 $23.04 \pm 1.38_{\text{ bc}}$		12%	4			54.54 ± 3.68		
12% 4 bc		6%	4	1.25 ± 0.02 ab	$119.37 \pm 23.02^{\text{ b}}$	42.20 ± 3.68	17.37 ± 1.38 d	
Significance	Fish oil 12%		4	1.20 ± 0.02 bc	163.21 ± 23.02 ab	43.36 ± 3.68		
Significance ** NS **	Cian:	ficones		0.001	0.042	0.076	0.000	
	Sigili	ncance		**	*	NS	**	

^{*} Significant at P < 0.05

^{**} Highly significant at P < 0.01

NS Not Significant

a, b and c means in the same coulmn with different superscripts were significantly different (P<0.05).

It can be concluded that using prepared fatliquor gave the same behavior and effects on collagen fiber like commercial fish oil fatliquor. Also, all leathers were similar in quality and suitable for leather manufacturing according to quality requirements for the main types of leather which observed by **BASF** (2007).

From the results in Table (8), chemical properties of finished calf leathers; from chemical properties of finished leathers, moisture contents and pH values were comparable among all finished leathers. On the other hand, ash and fat contents increased within each fatliquor group along with increasing fatliquors concentration, which was expected. With the exception of ash and fat content, the significant differences among values for chemical properties were not recorded, which demonstrates the similarity in tanning steps. High significant differences were found in ash content due to the ash content of added fatliquor, which was higher in prepared fatliquors than fish oil fatliquor as explained previously in table (6).

Table (8): Chemical properties of calf leathers.

• • • • • • • • • • • • • • • • • • • •		properties (or carried						
Item N		% Fat	% Moisture	% Ash	pН				
		Fatl	iquor effect						
or	6	7.10 ± 0.34	14.57 ± 0.3	5.90 ± 0.19	3.70 ± 0.03				
oha	6	7.14 ± 0.34	14.43 ± 0.3	5.56 ± 0.19	3.77 ± 0.03				
ing oil	6	6.64 ± 0.34	14.41 ± 0.3	5.66 ± 0.19	3.73 ± 0.03				
oil	6	7.19 ± 0.34	14.47 ± 0.3	5.52 ± 0.19	3.76 ± 0.03				
· C		0.653	0.980	0.571	0.271				
nicance		NS	NS	NS	NS				
Concentration Effect									
)	12	4.83 ± 0.24^{b}	14.37 ± 0.21	5.20 ± 0.14^{b}	3.72 ± 0.02				
	12	9.21 ± 0.24^{a}	14.56 ± 0.21	6.11 ± 0.14^{a}	3.76 ± 0.02				
G • • • • •		0.000	0.531	0.000	0.127				
nicance		**	NS	**	NS				
			action effect						
6%	3	$4.94 \pm 0.48^{\ b}$	14.78 ± 0.42	5.25 ± 0.28 bc	3.68 ± 0.04				
12%	3	9.25 ± 0.48^{a}	14.36 ± 0.42	6.51 ± 0.28^{a}	3.71 ± 0.04				
6%	3	4.70 ± 0.48 b	14.11 ± 0.42	5.16 ± 0.28 °	3.77 ± 0.04				
12%	3	9.57 ± 0.48^{a}	14.75 ± 0.42	5.95 ± 0.28 abc	3.77 ± 0.04				
6%	3	$4.73 \pm 0.48^{\text{ b}}$	14.08 ± 0.42	$5.19 \pm 0.28^{\text{ c}}$	3.65 ± 0.04				
12%	3	8.55 ± 0.48 ^a	14.74 ± 0.42	6.13 ± 0.28 ab	3.81 ± 0.04				
6%	3	4.92 ± 0.48 b	14.53 ± 0.42	5.18 ± 0.28 °	3.77 ± 0.04				
Fish oil 12%		9.45 ± 0.48 ^a	14.40 ± 0.42	5.86 ± 0.28 abc	3.75 ± 0.04				
ficence	•	0.000	0.857	0.015	0.119				
Significance		**	NS	*	NS				
	or oha ing oil oil ificance 6% 12% 6% 12% 6% 12%	N N N Or 6 Oha 6 Oha 6 Oha 6 Oha 6 Oha Oha	$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	Fatliquor effect or 6 7.10 ± 0.34 14.57 ± 0.3 5.90 ± 0.19 oha 6 7.14 ± 0.34 14.43 ± 0.3 5.56 ± 0.19 ing oil 6 6.64 ± 0.34 14.41 ± 0.3 5.66 ± 0.19 oil 6 7.19 ± 0.34 14.47 ± 0.3 5.52 ± 0.19 oil 6 7.19 ± 0.34 14.47 ± 0.3 5.52 ± 0.19 oil 6 7.19 ± 0.34 14.47 ± 0.3 6.52 ± 0.19 oil 16.53 0.980 0.571 NS				

^{*} Significant at P < 0.05

NS Not Significant

^{**} Highly significant at P < 0.01

a, b and c means in the same coulmn with different superscripts were significantly different (P<0.05).

On the other hand, the high significant differences of fat content were found due to concentration effect of adding fatliquores. Therefore, the increasing in the fatliquor concentration was corresponded with an increase in fat contents in finished leathers.

From chemical properties values, it can be concluded that all finished leathers were in acceptable range for using leathers in manufacturing, which explained by **BASF** (2007).

ACKNOWLEDGMENT

Authors would like to thank Eng. Mohamed El-Shafei, proprietor of El-Shafei son's tannery, Alexandria, Egypt for his help and support in the practical part.

REFERENCES

- **Adebowale, K. O. and C. O. Adedire (2006).** Chemical composition and insecticidal properties of the underutilized Jatropha curcas seed oil. *African Journal of Biotechnology*, 5(10): 901-906.
- **Akintayo, E. T.** (2004). Characteristics and composition of Parkia biglobbossa and Jatropha curcas oils and cakes. *Bioresource technology*, 92(3): 307-310.
- Akpan, U. G.; A. Jimoh and A. D. Mohammed (2006). Extraction, characterization and modification of castor seed oil. *Leonardo Journal of Sciences*, 8(1), 43-52.
- Allawzi, M.; M. K. Abu-Arabi; H. S. Al-Zoubi and A. Tamimi (1998). Physicochemical characteristics and thermal stability of Jordanian jojoba oil. Journal of the American Oil Chemists' Society, 75(1): 57-62.
- **ASTM (2010).** American Society for Testing and Materials. Books of standards vol.15.04.
- **BASF** (2007). Pocket book for leather technologist. 4th ed, 67056 Ludwigshafen, Germany.
- **Belitz, H. D.; W. Grosch, and P. Schieberle (2004).** Food Chemistry, 3rd ed. Springer-Verlag, Berlin., pp. 218–219.
- **Burgess, D.** (1994). General aspects of fatliquoring: an introduction to the application and chemistry of fatliquoring. Journal of the Society of Leather Technologists and chemists, 78(2): 39-43.
- **Covington, A. D. (2009).** Tanning chemistry the science of leather. RSC publishing, Cambrige, London.
- El-Shattory, Y.; G. A. Abo-ELwafa; S. M. Aly and E. S. H. Nashy (2012). Production of Ethoxylated Fatty Acids Derived From Jatropha Non-Edible Oil As a Nonionic Fat-Liquoring Agent. *Journal of Oleo science*, 61(5): 255-266.

- **Habib, M. A. and A. G. Alshammari (2017).** Recycling and utilization of waste deep frying oil in leather industry.
- **Idun-Acquah, N.; G. Y. Obeng and E. Mensah (2016).** Repetitive use of vegetable cooking oil and effects on physico-chemical properties—case of frying with redfish (Lutjanus fulgens). *SCI TECHNOLOGY*, 6(1): 8-14.
- **Kronick P. L.** (1998). Use of polymerizable oil for leather fatliquor. Washington, DC: U.S. Patent and Trademark Office 5, 853, 427.
- **Megahed, M. G. and E. H. A. Nashy (2010).** Ester phosphate of discarded palm oil from potato chip factories as fat-liquoring agent. *Journal of American Science*, 6(12): 617-626.
- Moreira, R. G.; M. E. Castell-Perez and M. Barrufet (1999). Deep fat frying: Fundamentals and applications. Boom Koninklijke Uitgevers.
- Nashy, E. S. H.; M. G. Megahed and M. A. Abd EL-Ghaffar (2011). Preparation of fat-liquor based on jojoba oil under phase transfer catalysis. Journal of the American Oil Chemists' Society, 88(8): 1239-1246.
- Omari, A.; E. B. Mubofu and Q. A. Mgani (2014). Fatty acid profile and physico-chemical parameters of castor oils in Tanzania.
- Romero, A.; S. Bastida and F. J. Sanchez-Muniz (2006). Cyclic fatty acid monomer formation in domestic frying of frozen foods in sunflower oil and high oleic acid sunflower oil without oil replenishment. Food and chemical toxicology, 44(10): 1674-1681.
- Shukla, Y. N.; A. Rani; A. K. Tripathi and S. Sharma (1996). Antifeedant activity of ursolic acid isolated from Duboisia myoporoides. *Phytotherapy Research*, 10(4): 359-360.
- **Tawfig, H.M.; G.A. Gasmelseed and F.E. Mohammed (2017).** Application of Fatliquor Prepared From Sudanese Castor Oil In Leather Fatliquoring Process. *International Journal of Engineering Sciences and Research Technology*, 6(10), 248-253.
- **Varnali, T. (2004).** What is leather? Bogazici Univ. Fac. Arts and Sci. Dep. Chem., Bebek 80815, Istanbul Turkey.
 - إستخدام بعض الزيوت الغير صالحة للأكل كمنتجات تشحيم في دباغة الجلود جمال صالح الفوال 1، زكريا عبدالرزاق نوفل 1، أحمد السيد خطاب 1، أحمد إبراهيم نصر 2
 - 1. قسم الكيمياء الحيوية ، كلية الزراعة ، جامعة الأزهر ، القاهرة، مصر.
 - 2. قسم إنتاج وتكنولوجيا الصوف، مركز بحوث الصحراء، القاهرة، مصر.

تؤثر مواد التشحيم على الخصائص الفيزيائية للجلد حيث تجعله أكثر ليونة ومرونة وقد أجريت هذه الدراسة لاستخدام بعض الزيوت النباتية الغير الصالحة للأكل مثل زيت الخروع والجاتروفا وزيت القلي المستخدم لتحضير مواد التشحيم التي يمكن استخدامها في

دباغة الجلود. تم استخلاص الزيوت المستخدمة في هذه الدراسة بواسطة الكبس الهيدروليكي الأوتوماتيكي. ثم تم تحضير مواد التشحيم عن طريق معاملة الزيوت بحامض الكبريتيك المركز. تم تحديد الخصائص الكيميائية للزيوت ومواد التشحيم المحضرة. تمت مقارنة مواد التشحيم المحضرة مع زيت السمك التجاري باستخدام تركيزين 6٪ و 12٪ من وزن الجلد. وقد تمت على جلود العجول بعد مرحلة الدباغة بالكروم لدراسة التغير في خصائص الجلد. أوضحت النتائج أن نسبة الدهون في بذور الخروع وبذور الجاتروفا تبلغ 29.94٪ و 51.67٪ على التوالي. كما كان محتوى الأحماض الدهنية غير المشبعة في الزيوت حوالي 67.13٪ و 81.28٪ و 50.10٪ في زيت الخروع والجاتروفا وزيت القلي المستخدم على التوالي ، وتشير قيمة الرقم اليودي إلى درجة إنصهار الزيوت المستخرجة لذلك تصنف الدهون والزيوت عادة على أساس قيمة الرقم اليودي إلى زيوت جافة وزيوت شبه جافة وزيوت غير جافة ؛ كما أن وجود الرابطة المزدوجة في الأحماض يسهل تفاعل السلفنة من خلال كسر تلك الرابطة واستكمال التفاعل وتحضير مواد تشحيم منها تدخل في صناعة دباغة الجلود. ومن خلال تطبيق ومقارنة مواد التشحيم المحضرة مع زيت السمك التجاري على جلود العجول كانت الجلود النهائية متشابهة في الجودة ويمكن استخدامها في أغراض مختلفة من صناعة الجلود. لذلك توصى الدراسة باستخدام الزيوت غير الصالحة للأكل في تصنيع مواد تشحيم تستخدم في صناعة الجلود وذلك لتقليل تكاليف الإنتاج وتقليل التلوث الناتج عن التخلص غير الآمن منها.